

FLASHING ADHESIVE

Description

Elastomer base contact adhesive for bonding membranes (versions without nonwoven fabric backing) to clay masonry, wood, metal and other suitable substrates^(*).

Note: (*) FLASHING ADHESIVE is compatible with most solvent-resistant substrates. However, it is advisable to perform a preliminary trial to confirm compatibility. For more information, consult the RUBBERFUSE Division Technical Services.

Features

Solid content

43%

Viscosity (20°C)

2,500 m Pa s

Density

0.865 kg/dm³

Shelf-life

1 year. Store in a cool dry place, at temperatures not above 25°C.

Packaging

- 20 kg bucket, 24 buckets per pallet.
- IMO data “flammable liquid adhesive”:
ADR no. 3
UN 1133
Kemmler Index 33
Group III
Flash point <23°C

Yield

0,4-0,6 kg/m² (Consumption can increase, on wood or concrete, depending on the porosity of the substrate itself).

Application

- Use outdoors or in a well-ventilated area.
- Apply at temperatures above 5°C. If necessary, heat container in hot water at about 50°C.
- The substrate must be clean, dry and uncontaminated.
- Mix before using.
- Using a brush or roller, apply a thin, even coat of adhesive to both the membrane and the substrate, avoiding excess buildup. Allow to dry. When adhesive is dry to touch, place membrane in contact with substrate and apply pressure.
- Do not thin. Clean tools with ethyl acetate or with petrol.
- See RUBBERFUSE Division specifications and instructions.

Safety regulations

- Avoid contact with skin. Wash with water and soap.
- In case of contact with eyes, rinse immediately with plenty of water.
- When using do not eat, drink or smoke.
- Do not inhale. In case of inhalation symptoms, consult a doctor.
- Fire: put out with water or with CO₂ foam.
- Refer to the safety data sheet.

Rev. 00 (11-15)

As IMPER ITALIA srl has no control over how or where its products are supplied (e.g., over substrates, service conditions, or compliance with instructions), the company cannot accept any liability arising from the use of its product or the results obtained. IMPER ITALIA srl pursues a policy of continuous product improvement. As a result, the company reserves the right to make any necessary changes to the information contained in this publication at any time and without notice.

ISO 9001
ISO 14001
OHSAS 18001
BUREAU VERITAS
Certification



Imper Italia srl Via Volta, 8 · 10071
Frazione Mappano · Borgaro (TO) Italy
Tel (+39) 011 222.54.99 · Fax (+39) 011 222.54.80
export@imper.it · www.imper.it